

Tolonate[®] IDT 70 B



Description

- ⇒ Aliphatic polyisocyanate based on Isophorone Diisocyanate trimer (IPDI homopolymer), supplied at 70 % solids in butyl acetate.

Suggested Uses

- ⇒ Two-component polyurethane coatings and varnishes, showing an excellent weathering resistance.
- ⇒ Exterior protective coatings for automotive OEM and car repair, general industrial, plastics, wood...etc.

Specifications

Colour	≤ 60 HAZEN (APHA)
Viscosity at 25°C	600 ± 300 mPa.s
NCO (on delivery form)	12.3 ± 1.0 %
Solids content	70.0 ± 2.0 %
Isophorone diisocyanate monomer (IPDI)	< 0.5 %

The analytical methods are available upon request

Physical Properties

Appearance	Clear liquid
Bulk density at 25°C	1060 kg/m ³ approx.
Weight per US gallon	8.85 lbs approx.
Flash point (closed cup)	29°C approx.
Equivalent weight (on delivery form)	342 g approx.

Solubility

Soluble in esters, ketones, aromatic hydrocarbons. In most cases, esters/aromatic hydrocarbon mixtures are used.

It is recommended to use "urethane grade" solvents for the dilution (with water content below 300 ppm).

Tolonate[®] IDT 70 B

Applications

- ⇒ **TOLONATE[®] IDT 70 B** is typically used as a crosslinker of hydroxylated polymers, especially polyesters and polyacrylic polyols, to prepare two-component polyurethanes coatings and varnishes showing excellent outdoor durability and mechanical properties in conjunction with outstanding resistance to solvents, abrasion and chemicals.
- ⇒ Due to its cycloaliphatic structure, TOLONATE[®] IDT 70 B is usually used in blends with HDI derivatives, such as, for instance, TOLONATE[®] HDB 75 MX, TOLONATE[®] E HDT 90 or TOLONATE[®] HDT-LV2. Recommended ratios are usually in the range of 80/20 to 60/40 (HDI derivative / IDT - dry/dry). Using TOLONATE[®] IDT 70 B in the hardener leads to films with shorter physical drying and higher hardness.

Packaging and transport

Packaging (please contact our sales team for more details)

- ⇒ Deliveries of 800 kg net weight pallets (4 drums of 200 kg net weight).
- ⇒ Other packaging: upon request

Transport

- ⇒ Regulated. For more precise details, please refer to the safety data sheet

Storage conditions and shelf-life

- ⇒ TOLONATE[®] IDT 70 B is sensitive to moisture and should be kept in its original container or in a volume tank under dry nitrogen blanketing, for example.
- ⇒ Appropriate storage for 1 year does not normally affect the product in any way if it is stored in its sealed original drums in proper storage conditions at temperatures below 40°C.

Inflammability and safety instructions

- ⇒ Before handling this product please refer to its safety data sheet

WARNING TO USERS

The information contained in this document is given in good faith and based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third parties through the use of our products. PERSTORP guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are responsible for ensuring compliance with local regulation and for obtaining the necessary certifications and authorizations.

Users are requested to check that they are in possession of the latest version of the present document and PERSTORP is at their disposal to supply any additional information.

TOLONATE[®] is a registered mark of PERSTORP.