

Polyol R3430



Description

- Polyol R3430 is an alkoxyated polyol
- Trifunctional with primary hydroxyl groups
- Liquid

Applications

- Precursor for free radical radiation curing monomers and oligomers
- Chemical building block

Delivery forms

- Steel drums 200 kg, 800 kg/pallet
- Bulk at approximately 50°C

Sales specification

Hydroxyl number, mg KOH/g ¹	425 ± 20
Water content, % ²	Max. 0.3

Typical properties

Molecular weight (nominal), g/mole	398 *
Ash content (Na+K), ppm ³	400
Colour, APHA ⁴	30
Viscosity (23 °C), mPas ⁵	400
Acid number, mg KOH/g ⁶	0.1

*information only

Analytical Method

¹ PO 100-1, ² PO 109-2, ³ PO 103-3, ⁴ PO 105-4, ⁵ PO 120-2, ⁶ PO 110-1
Analytical methods are available on request

REACH Exempt Polymer
HS no.: 3907 20

Valid from: December 28, 2011
Supersedes: January 1, 2006/b