# Boltorn<sup>TM</sup> dendritic polymers

Advancing performance & comfort





# The cutting edge of technology

Whether you are looking to secure firmness in flexible polyurethane foam, improve the Tg/flexibility ratio of cast polyurethane elastomer products, ensure rapid curing and durability in UV curing applications or reduce VOC in architectural coatings, dendritic polymers are a solution.

Dendric polymers are characterized by a densely branched backbone and a large number of reactive groups. Their globular structures have excellent flow and processing properties at high molecular weight. The exceptional concentration of reactive groups facilitates customization of properties for a wide range of end uses.

## Main applications

- Performance additives for flexible polyurethane foam, such as in automotive seating applications
- Oligomer precursors for UV-curing applications for excellent scratch resistance, adhesion and flexibility
- Water-dispersing additives for partial replacement of solvents with water in solvent-borne paints
- Reactive diluents for VOC control with maintained • drying properties in high-solid alkyd paints

You can tailor make Boltorn™ products by utilizing our unique technology. For further information please visit www.perstorp.com or contact one of our specialists to discuss your requirements in more detail.

## Boltorn™ dendritic product range


Boltorn<sup>™</sup> products are produced using polyalcohol cores, hydroxy acids and technology based on captive materials. The dendritic structures are formed by polymerization of the particular core and 2,2-dimethylol propionic acid (Bis-MPA). The base products obtained are hydroxyl-functional dendritic polyesters. Fully aliphatic and consisting only of tertiary ester bonds, they provide excellent thermal and chemical resistance. Extensive branching also improves reactivity, lowers viscosity and results in balanced mechanical properties.

### Three technology advantages

- 1. Large number of primary hydroxyl groups
- 2. Densely branched polymer backbone
- 3. Extensive formulation possibilities

#### **PRODUCT CHARACTERISTICS**

| Product        | Main haracteristics  | Nominal molecular weight |
|----------------|--|--------------------------|
| Boltorn™ H2004 | 6 terminal hydroxyl groups                                   | 3,100 g/mol              |
| Boltorn™ H311  | 23 terminal hydroxyl groups                                  | 5,300 g/mol              |
| Boltorn™ P500  | Formulated bimodal product with terminal hydroxyl groups     | 1,800 g/mol              |
| Boltorn™ P1000 | Formulated bimodal product with terminal hydroxyl groups     | 1,500 g/mol              |
| Boltorn™ U3000 | Modified with unsaturated fatty acid                         | 6,500 g/mol              |
| Boltorn™ W3000 | Modified with non-ionic groups<br>and unsaturated fatty acid | 10,000 g/mol             |





## Use case Polyurethanes


Millions of car owners already enjoy superior seating comfort with the help of Boltorn<sup>™</sup> technology. In partnership with a leading automotive foam supplier, we have developed a unique technology that improves the firmness of high-resilience foam articles with dendritic polymer polyols.

## Products in focus

#### Boltorn™ H311 – for exceptional firmness & stability

This liquid polymer polyol provides exceptional compressive loadbuilding characteristics in flexible foam at very low addition levels. It is used as an additive, partially replacing conventional cross-linkers or graft co-polymer polyols of SANtype. Compared to conventional technology, Boltorn™ H311 offers considerable benefits:

- Two to three times the efficiency in providing compressive loads (IFD or CFD) at a given addition solids level, which allows lower average solids levels to be used
- Exceptional firmness, extending beyond current state-of-the-art technology
- Improved foam stability due to the cross-linking mechanism and reduced surface voids of finished parts



Compressive load as function of polymer content for Boltorn<sup>™</sup> H311 vs. co-polymer polyols

### Boltorn™ P500 – for high firmness at low compression set

Our dendritic polymer polyol for molded foam is a product that yields exceptionally low compression set at high firmness when used with graft co-polymer polyols. The low compression set

allows you to operate at reduced foam density and still meet the comfort specifications of end users.

| Formulation                | 60-15 | 50-11-4 |
|----------------------------|-------|---------|
| SAN, %                     | 15    | 11      |
| Boltorn™ P500, %           | 0     | 4       |
| Density, kg/m <sup>3</sup> | 60    | 50      |
| IFD-25, N                  | 239   | 192     |
| IFD-65, N                  | 633   | 558     |
| Dry set, %                 | 4     | 2.9     |
|                            |       |         |

Standard high resiliance molded formulation. Density reduction at reduced compression set when using Boltorn<sup>™</sup> P500.



## Use case Radiation curing

Boltorn<sup>™</sup> products enhance radiation curing applications by providing oligomer precursors that significantly increase the average molecular weight of UV formulations at high acrylate concentration. Acrylates based on Boltorn<sup>™</sup> technology are typically used to partially or fully replace urethane acrylates, other top-end oligomers or acrylates of high functionality.

#### Oligomer precursors for superior performance

Acrylate oligomers based on Boltorn<sup>™</sup> dendritic polyols offer significant benefits:

- Excellent reactivity
- Improved scratch resistance and film hardness
- Low shrinkage and good adhesion
- Exceptional flow properties and good pigment wetting
- Improved labeling with low extractables
- Unique molecular weight/viscosity ratio

For coatings, the balance between flow and properties like reactivity, and chemical and scratch resistance, is crucial for meeting end-user demands. Environmental compliance is also a key competitive factor. Radiation curing systems, typically UV, have gained market share in the past decades since very rapid curing and excellent film properties are obtained with low or no VOC emissions.

## Products in focus

#### Boltorn<sup>™</sup> P500 - designed for hardness

Boltorn™ P500 has been specifically tailored to offer a good balance between hardness and flexibility. The acrylate of Boltorn™ P500 achieves an ideal balance between hardness, flexibility and reactivity together with a low viscosity.

## Boltorn<sup>™</sup> P1000 – for monomer free formulation

Boltorn<sup>™</sup> P1000 is a low-viscosity polymer polyol allowing monomer-free formulation. It combines the low viscosity and low shrinkage with high reactivity required in applications such as UV digital printing.

#### Boltorn<sup>™</sup> H2004 – improves ink flow

This dendritic polyol not only offers the general advantages of polyols in cationic systems like improved flexibility, but also further improves the chemical resistance and rheological behavior of flexographic inks while maintaining high curing speed. The Newtonian behavior of printing inks containing Boltorn™ H2004 improves ink transfer at high speeds.

|  | DPHA        | Boltorn™<br>P500 acrylate |  |  |
|--|-------------|---------------------------|--|--|
| Viscosity, 100% solids<br>(mPas, 23°C)           | 12,800      | 500                       |  |  |
| Pencil hardness on PC                            | 5H/6H       | H/2H                      |  |  |
| Adhesion crosscut on PC                          | Fail (GT-5) | OK (GT-0)                 |  |  |
| Steel wool rubs (50 rubs)<br>on PC, gloss 20°, % | 98,5        | 95.7                      |  |  |

Both coating formulations contain 4% Irgacure 250, are applied 6  $\mu m$  thick on Polycarboate and cured by using 250 mJ/cm²



## Use case Architectural coatings

Boltorn<sup>™</sup> performance additives for solvent-borne and waterborne architectural coatings help coating formulators comply with environmental demands without compromising coating performance. A number of patented technologies have been developed in which Boltorn<sup>™</sup> additives improve the performance of architectural coatings. You can achieve the required coating properties while reducing VOC. Further on, with Boltorn<sup>™</sup> you get improved drying in wood stain and reduced cost at lower VOC in water-extended solvent-borne paints.


## Products in focus

#### Boltorn<sup>™</sup> U3000 – unique flow properties

For high-solid alkyds, the branched structure of Boltorn™ U3000 provides unique flow properties, which allows woodstains and alkyd paints for outdoor applications to comply with recent VOC demands while still securing rapid drying and durability.

## Boltorn™ W3000 – add 1% and gain 10%

The unique properties of dendritic polymers offer extensive design possibilities. With Boltorn™ W3000, we have developed a water-dispersing additive that contains non-ionic as well as unsaturated fatty acid chains. This highly efficient product allows paint formulators to partially exchange solvent for water. By adding approx. 1% of Boltorn™ W3000 to a solvent-borne paint, 15% of the solvent can be replaced with water. The resulting paint will have a similar paint performance at a lower cost per liter and with reduced air emissions.



Schematic structure of Boltorn<sup>™</sup> W3000

| Formulation           | Conventional<br>woodstain | +40wt%<br>Boltorn™ U3000  |  |
|-----------------------|---------------------------|---------------------------|--|
| Туре                  | oil/alkyd                 | oil/alkyd/dendritic alkyd |  |
| VOC, g/l              | 595                       | 238                       |  |
| Viscosity, 23°C, mPas | 28                        | 72                        |  |
|                       | ^                         |                           |  |

| Drying properties (45µm dry film) |    |    |  |  |  |
|-----------------------------------|----|----|--|--|--|
| Film hardness-1 day, Ks           | 5  | 45 |  |  |  |
| Film hardness-10 days, Ks         | 27 | 35 |  |  |  |
| Film hardness-17 days, Ks         | 27 | 33 |  |  |  |
| Film hardness-31 days, Ks         | 26 | 33 |  |  |  |

Effect on VOC and drying properties when adding Boltorn  $^{\rm \tiny M}$  U3000 to a conventional woodstain available in Scandinavia

| High-gloss paint for brush application   | Water-extended<br>paint with<br>Boltorn™ W3000 | Solvent-borne<br>alkyd paint<br>reference |
|--|--|---|
| Boltorn <sup>™</sup> W3000, wt% in paint | 1.34   | -   |
| Alkyd (OL65), wt% in paint               | 27.8   | 33.1                                      |
| Water content, wt% in paint              | 15.1   | -   |
| PVC, wt%                                 | 18.7   | 18.7                                      |
| VOC, g/l                                 | 340  | 420                                       |
| Gloss, 60°, %                            | 94   | 92  |
| Drying*                                  |  |   |
| Dust dry, h                              | 0.5  | 0.5                                       |
| Tack-free, h                             | 2.5  | 2.5                                       |
| Through-dry, h                           | 3.0  | 3.0                                       |
| Hard, h                                  | 3.5  | 7.0                                       |

\* Beck-Koller, glass panels at 23°C, 50% humidity, 25 µm DFT

The physical properties of a water-extended solvent-borne alkyd paint containing Boltorn<sup>™</sup> W3000 compared to a solvent-borne counterpart

#### Product data summary

| Product                   | Soluble in                      | Appearance    | Water cont.<br>wt% | OH-value<br>mg KOH/g | Mw (GPC) g/mol | Tg<br>(DMA) °C | Viscosity,<br>Pas (°C) |
|---------------------------|---------------------------------|---------------|--------------------|----------------------|----------------|----------------|------------------------|
| Molded flexible foa       | m                               |               |                    |                      |                |                |                        |
| Boltorn <sup>™</sup> H311 | Polyether/<br>polyester polyols | Yellow liquid | 9.5 – 10.5         | 230 – 260            | 5,700          | -5             | 40 (23)                |
| Boltorn <sup>™</sup> P500 | Polyether polyols               | Clear liquid  | <0.5               | 560 – 630            | 1,800          |                | 15 (23)                |

| Product                    | Soluble in                | Appearance    | Functionality     | OH-value<br>mg KOH/g | Mw (GPC) g/mol  | Tg<br>(DMA) °C | Viscosity,<br>Pas (°C) |
|----------------------------|---------------------------|---------------|-------------------|----------------------|-----------------|----------------|------------------------|
| Radiation curing           |                           |               |                   |                      |                 |                |                        |
| Boltorn <sup>™</sup> P500  | Acrylic acid<br>+ toluene | Clear liquid  | Mixed<br>hydroxyl | 560 – 630            | 1,800 (bimodal) | -              | 12 (23)                |
| Boltorn <sup>™</sup> P1000 | Acrylic acid<br>+ toluene | Clear liquid  | Mixed<br>hydroxyl | 430 – 490            | 1,500 (bimodal) | _              | 5 (23)                 |
| Boltorn <sup>™</sup> H2004 | EtOH, Toluene,<br>Xylene  | Yellow liquid | 6                 | 105 – 125            | 3,200           | -35            | 15 (23)                |

| Product              | Soluble in  | Appearance    | Functionality             | Oil length<br>% triglyc.   | Mw (GPC) g/mol | Solids, % | Viscosity,<br>Pas (°C) |
|----------------------|---|---------------|---------------------------|----------------------------|----------------|-----------|------------------------|
| Architectural, water | rborne coatings   |               |                           |                            |                |           |                        |
| Boltorn™ U3000       | Oils, coalescents,<br>EtOH, Xylene                        | Yellow liquid | Air-drying                | 75                         | 6,500          | 99        | 1 (23)                 |
| Boltorn™ W3000       | Emulsifying,<br>soluble in alkyds,<br>co-solvents, xylene | Yellow wax    | Amphiphilic<br>Air-drying | 45<br>(fully<br>aliphatic) | 9,000          | 99        | 2 (35)                 |



# One molecule can change everything

Perstorp believes in improving everyday life – making it safer, more convenient and more environmentally sound for billions of people all over the world. As a world leading specialty chemicals company, our innovations provide essential properties for products used every day and everywhere. You'll find us all the way from your car and mobile phone to towering wind turbines and the local dairy farm. Simply put, we work to make good products even better, with a clear sustainability agenda.

Perstorp's focused innovation builds on more than 135 years of experience, representing a complete chain of solutions in organic chemistry, process technology and application development. Manufacturing is based in Asia, Europe and North America, with sales and support in all major markets. The Perstorp Group is controlled by funds managed and advised by the European private equity company PAI partners.

Learn more at www.perstorp.com

